

MARIPUR® 7200

Aliphatic Polyurethane Floor Coating UV-stable

Product description

The MARIPUR® 7200 is a colored, one component, highly durable, aliphatic polyurethane thin-layer floor coating. The MARIPUR® 7200 is specially designed for use as a floor coating in external surfaces, providing high mechanical strength, high abrasion and chemical resistance. It is color stable, UV-stable and weather-stable so it can withstand the battering of the elements when applied outside.

The MARIPUR® 7200 is using a unique curing system (moisture triggered), and unlike other similar systems it does not react with moisture (moisture-cured) and therefore does not form bubbles or blisters when applied in higher thicknesses.

Uses

The MARIPUR® 7200 is mainly used on concrete floors, on exterior or interior surfaces. Due to its long lasting unchangeable properties is widely used for:

- Car parking areas,
- Show rooms,
- External and Internal Pedestrian Decks,
- Storage rooms,
- Warehouses,
- Factories, etc.

Advantages

- Simple application (roller or airless spray).
- Decorative.
- Resistant to constant, heavy abrasion and wear conditions.
- Color stable and UV stable.
- Heat and frost resistant
- When applied does not absorb liquids or dirt.
- Stops the creation of dust.
- Gives a glossy and easy-to-clean surface.
- Does not show the chalking effect of aromatic polyurethane waterproofing coatings.
- Chemical resistant.
- Maintains its mechanical properties over a temperature span of -20°C to +90°C.

Consumption

400 gr/m² in two layers. This coverage is based on practical application by roller onto a smooth surface in optimum conditions. Factors like surface porosity, temperature, humidity, application method and finish required can alter consumption.

Colors

The MARIPUR® 7200 is supplied in light grey, dark grey and beige. Other RAL colors supplied on request.

Technical data*

PROPERTY	RESULTS	TEST METHOD
Composition	Pigmented Aliphatic Polyurethane pre-polymer. Solvent based	
Elongation at Break	>100 %	DIN 53504
Tensile Strength	>5 N/mm ²	DIN 53504
Adhesion to Concrete	>2 N/mm ²	ASTM D 903
UV and Color stability	excellent	Inhouse Test
Hardness (SHORE D Scale)	20	ASTM D 2240
Resistance to Water Pressure	No Leak (1m water column, 24h)	DIN EN 1928
Application Temperature	5°C to 35°C	Conditions: 20°C, 50% RH
Tack Free Time	3-5 hours	
Light Trafficking	12-24 hours	
Final Curing time	7 days	

Chemical properties**

Potassium hydroxide 5%	+	Sodium hydroxide 5%	+
Ammonia 5%	+	Sulfuric acid 5%	+
Hydrochloric acid 5%	+	Sea water	+
Domestic detergents (diluted)	+	Dichlormethane	-
Diesel fuel	+	N-methyl pyrrolidone (brake fluid)	-

{+ Stable, - Not stable, ± Stable for a short period.

Application

Surface Preparation

Careful surface preparation is essential for optimum finish and durability.

The surface needs to be grinded with a stone- or a diamond-grinding machine. The surface needs to be clean, dry and sound, free of any contamination, which may harmfully affect the adhesion of the coating. Maximum moisture content should not exceed 5%. Substrate compressive strength should be at least 25MPa, cohesive bond strength at least 1.5MPa. New concrete structures need to dry for at least 28 days. Old coatings, dirt, fats, oils, organic substances and dust need to be removed by a grinding machine. Possible surface irregularities need to be smoothed. Any loose surface pieces and grinding dust need to be thoroughly removed.

WARNING: Do not wash surface with water!

WARNING: Do not use a metal-ball blasting machine to grind the surface, because the heavy metal-ball impacts destroy the cohesion of the concrete surface and lower its stability.

Repair of cracks:

Clean cracks and hairline cracks, of dust, residue or other contamination. Fill all cracks with suitable putty. The next day smoothen the putty surface with a sandpaper or a mechanical grinder.

Absorbent surfaces

Prime absorbent surfaces, like concrete, cement screed and wood with the MARIPUR® 7000 primer, for the first layer by using a roller, brush or a spray gun.

After 2-3 hours (not later than 4 hours) and while the primer is still a bit tacky, apply the first layer, of the coloured MARIPUR® 7200 coating.

Once again allow 3-4 hours for the coating to cure (not more than 4 hours) and apply the second layer of the coloured MARIPUR® 7200.

Non-absorbent surfaces

Prime non-absorbent surfaces like metal, terrazzo, mosaic, power-floated concrete and ceramic tiles with the MARISEAL-AQUA PRIMER (diluted 25-30% with water), for the first layer by using a roller, or a brush.

After 12 hours (not later than 18 hours) apply the first layer, of the coloured MARIPUR® 7200 coating.

Once again allow 3-4 hours for the coating to cure (not more than 4 hours) and apply the second layer of the coloured MARIPUR® 7200.

Stir well before using. For best results, the temperature during application and cure should be between 5°C and 35°C. Low temperatures retard cure while high temperature speed up curing. High humidity may affect the final finish.

Anti-slip Finish

In order to achieve an anti-slip effect we need to evenly sprinkle corundum (or silica sand) on the first layer of MARIPUR® 7200 while still wet. When the layer is dry, we brush off any excess aggregate and continue with the application of the second layer of the MARIPUR® 7200.

Packaging

MARIPUR® 7200 is supplied in 20 kg, 10 kg, 5 kg and 1kg pails. Pails should be stored in dry and cool rooms for up to 9 months. Protect the material against moisture and direct sunlight. Storage temperature: 5°-30°C. Products should remain in their original, unopened containers, bearing the manufacturers name, product designation, batch number and application precaution labels.

Safety measures

MARIPUR® 7200 contains isocyanates. See information supplied by the manufacturer. Please study the Safety Data sheet. **PROFESSIONAL USE ONLY.**

Our technical advice for use, whether verbal, written or in tests, is given in good faith and reflect the current level of knowledge and experience with our products. When using our products, a detailed object-related and qualified inspection is required in each individual case in order to determine whether the product and /or application technology in question meets the specific requirements and purposes. We are liable only for our products being free from faults; correct application of our products therefore falls entirely within your scope of liability and responsibility. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery. Users are responsible for complying with local legislation and for obtaining any required approvals or authorizations. Values in this technical data sheet are given as examples and may not be regarded as specifications. For product specifications contact our R+D department. The new edition of the technical data sheet supersedes the previous technical information and renders it invalid. It is therefore necessary that you always have to hand the current code of practice.

* All values represent typical values and are not part of the product specification. ** Chemical resistance tests time : 24hours